

## **BOILER PIPES**

### **AREAS OF APPLICATION**

It is used in the transmission of flammable and non-explosive liquids at high temperature and pressure.

### **Production Range**

- Outer Diameter 21.3 mm - 339.7 mm
- Wall Thickness 2.6 mm - 13 mm
- Length 4-14 m (standard)

### **Technical Specifications**

- Wall Thickness  $t \leq 5$ ,  $\pm 1\%$  or  $\pm 0.5$  mm
- Outer Diameter (d) tolerance  $d \leq 339.7$ ,  $\pm 1\%$  or  $\pm 0.5$  mm (whichever value is greater)  $d > 339.7$ ,  $\pm 0.75$  mm
- Length tolerance is -0, + 15 mm.
- Internal burrs are removed.
- It is varnished.
- It passes 100% magnetic test (Eddy Current and Ultrasonic test).

### **Production Standards**

- TS EN 10217-2, P 235GH (st 37.8) and higher quality material.

P265 GH,16Mo3

## KAZAN BORULARI

<b>İç/Dış Çap mm</b>	<b>ET KALINLIK mm</b>	<b>1 mt./Kg.</b>
39.5/44.5	2.5	2.600
46/51	3.0	3.600
51/57	3.0	4.000
57/63	3.0	4.500
64/70	3.0	4.950
70/76	3.0	5.450
76/83	3.25	6.460
83/89	3.25	6.850
95/102	3.75	9.100
102/108	3.75	9.700
108/114	3.75	10.200
119/127	4.0	12.200
125/133	4.0	12.700
133/140	4.0	13.500
150/159	4.5	17.200